



## Product Data Sheet & General Processing Conditions

### RTP 1503-55D Polyether-Ester Block Copolymer (TEEE/COPE) Glass Fiber

#### PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.35	1.35	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0017 - 0.0025 in/in	0.17 - 0.25 %	D 955
<b>MECHANICAL</b>			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	6.4 ft-lbs/in	342 J/m	D 256
unnotched 1/8 in (3.2 mm) section	20.0 ft-lbs/in	1068 J/m	D 4812
Tensile Strength	6250 psi	43 MPa	D 638
Tensile Elongation	8.8 %	8.8 %	D 638
Tensile Modulus	0.33 x 10 <sup>6</sup> psi	2275 MPa	D 638
Flexural Strength	7250 psi	50 MPa	D 790
Flexural Modulus	0.24 x 10 <sup>6</sup> psi	1655 MPa	D 790
Hardness			
Shore D, instantaneous	65	65	D 2240

#### PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

#### GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Melt Temperature	430 - 480 °F	221 - 249 °C
Mold Temperature	70 - 120 °F	21 - 49 °C
Drying	2 - 3 hrs @ 212 °F	2 - 3 hrs @ 100 °C
Moisture Content	< 0.10 %	< 0.10 %

#### PROCESSING NOTES

Desiccant Type Dryer Required.

12 Nov 2014 SDB

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate

under, or a recommendation to infringe any patents.

RTP COMPANY • 580 EAST FRONT STREET • WINONA, MN 55987 • 507-454-6900